



MDI TERMINATED POLYESTER PREPOLYMER DATA SHEET

TYPICAL PHYSICAL PROPERTIES WITH:	1,4 BDO	
HARDNESS	SHORE A	85
RESILIENCE	% REBOUND	35
SPLIT TEARS STRENGTH	PLI	350
DIE C TEAR STRENGTH	PLI	520
TENSILE STRENGTH	PSI	7000
ULTIMATE ELONGATION	%	600
100% MODULUS	PSI	770
200% MODULIS	PSI	1130
300% MODULIS	PSI	1668
COMPRESSION SET	%	28
COMPRESSION DEFLECTION	15%	500
TABER ABRASION	Mg LOSS	16

